

PROPERTY	ADC	PC	PMMA
TRANSMISSION, VISIBLE (%) 400-700 NM	92	90	90
TRANSMISSION, INFRARED (%) 700-1100 NM	89-92	85-89	85-89
REFRACTIVE INDEX	1.501	1.586	1.46
HAZE (%)	0.21	1.00	2.00
YELLOWNESS INDEX	0.73	1.00	2.00
DISPERSION FACTOR (ABBE NUMBER)	59.2	24.8	57.2